INTERNATIONAL PAPER

Technical Characteristics

TO : IPEX

ATT. : Controle de Qualidade

DATE : 20/03/2015 ***Alkaline Paper***

		Minimum	Target	Maximum		
Brightness Felt(S/F)	ISO	96,0	98,0		ISO-2470	C
Grammage	g/m²	72,0	75,0	78,0	ISO-536	C
Moisture	%	3,9	4,4	4,9	ISO-287	C
Opacity	%	86,0	90,0		ISO-2471	C
Porosity Gurley	s/100cc	7,0	10,0	14,0	TAPPI-460	C
Roughness Bendtsen W	mL/min	80,0	140,0	200,0	ISO-8791	C
Roughness Bendtsen-F	mL/min	170,0	255,0	340,0	ISO-8791	C
Stiffness CD	gf.cm	0,8	1,0		ISO-2493	C
Stiffness MD	gf.cm	1,890	2,100		ISO-2493	C
Thickness	mm	0,092	0,097	0,102	ISO-534	C
Whiteness Felt	D65 10°	158,0	161,0	164,0	ISO-11475	C

Sincerely

RAFAEL RODRIGUES

Quality Control

PAPER - OFFICE DEPOT 75.0
Shade
Conditioning of samples

Standard IPB
ISO 187/00
CED075 - Rev. 86 - STD